

Breathable and algacide paint for swimming pools

MAIN USES

Waterproof paint for pools, water tanks, basements, canals, drains, cisterns and any location permanently or sporadically covered in water.

PROPERTIES

Breathable.
Adheres to all types of new concrete. Also on old, previous corresponding preparation.
Easy maintenance.
Chlorine and salt resistant.
Slows the formation of algae.

LIMITATIONS

It cannot be painted on flexible mortars, waterproofing membranes or other soft supports because it may crack during drying.

It is recommended to paint thin coats to facilitate the breathability of the finish and avoid finishing problems.

LIQUID PAINT TECHNICAL INFORMATION

Specific Weight 1.4 kg / litre
Type of diluent **DISOLSINT**
Sedimentation Does not form skin or pores.

DRY PAINT TECHNICAL INFORMATION

Colour White and blue
Aspect Anti-slip
Finishing Matt

TECHNICAL INFORMATION FOR APPLICATION

Dilution 1st layer 15-20%, 2nd layer 10-15%.
Performance 10 m2/liter/layer, approximately.
Application methods: A roller is the best application system, but the product can be applied by brush or spray gun (NOT AIRLESS).
It is thixotropic, so it will not drip or sag.
Clean utensils with **DISOLSINT** solvent.
Application conditions:
Supports Clean, dry and free of grease and dust.
Environmental Good air renewal in enclosed spaces.
Unaffected by atmospheric conditions.

ACUARIS ANTIALGAS

09131

SUPPORTS: CONDITIONS AND TREATMENTS

Compatibility with other layers:

Previous layers Not necessary.
Subsequent layers The same paint.

Surface preparations:

New concrete As long as the concrete has absorption, directly apply two coats of ACUARIS ANTIALGAS.
Old painted concrete Brush to remove chipped or flaky paint.
Wash away scum and algae with **SANEART S**, then apply two coats of **ACUARIS ANTIALGAS**.

For the painting of other materials or in situations not covered by this technical sheet, please consult our Commercial Technical Service.

DRYING TIMES

Conditions:

Ambient temperature 20 °C
Relative humidity 70 %

<u>Total Drying Time</u>	<u>Interval Between Coats</u>	
	<u>Minimum</u>	<u>Maximum</u>
24 hours	4 hours between coats	unlimited
The pool can be filled after 72 hours.	Perfect adhesion on previous coats of ACUARIS ANTIALGAS , after 2 or more years of use.	

STORAGE AND PACKAGING

Supply format In silk-screened metal cans containing 0.750, 4 and 15 litres.
Storage In closed original packaging at temperatures of +5°C to +40 °C.
Expiry 2 years from the shipping date, in original unopened packaging.

SAFETY AND THE ENVIRONMENT

Read the packaging label and the Safety Sheet.



ER 0447/2012

Servicio de atención al cliente y asistencia técnica
973-45 07 17
CTRA. DE GERB, 51-73 • 25600 BALAGUER (Lleida) • España • UE
• e-mail: info@articsa.net • www.articsa.net

Rev. June 22